

# TECHNICAL DATA SHEET

## SEKU-MIX® 200

### Description

The Seku-mix® 200 ready-made diaphragm wall building material is designed as the economical version for tasks such as enclosing excavations and hydraulic engineering. By choosing the appropriate modifications, Seku-mix 200 can be individually tailored to the requirements of the building project.

**Formulation:** 200 kg Seku-mix  
≈ 922 liter water

**Suspension density** ≈ 1.120 t/m<sup>3</sup>

### Rheology:

**Marsh viscosity**  $t_{0h}$  36 – 46 s (based on DIN 4127: 2014-02)  
 $t_{8h}$  < 60 s (stirring test according to GDA requirements at 10 °C)

**Yield stress** > 20 N/m<sup>2</sup> (in accordance with DIN 4127: 2014-02)

**Filtrate loss** < 70 ml (in accordance with DIN 4127: 2014-02)

**Sedimentation**  $t_{24h}$  < 3 % (internal test instruction PA 610)

**Compressive strength:** **Cylinder compressive strength at 20 °C** (based on DIN EN ISO 17892-7:2018)

28 d
≈ 575 kN/m <sup>2</sup>

**Permeability:** **Coefficient of permeability (k value)** (in accordance with DIN EN ISO 17892-11:2019)

Measuring equipment: triaxial cell; i = 30

28 d
≤ 1 x 10 <sup>-9</sup> m/s

Status: May 2023

Page 1 of 1

The above data relate to tests under laboratory conditions with the usual metrological tolerances. These along with records of other "suitability tests" are designed to obtain information about the basic suitability of our product in respect of the intended purpose. Even in the case of a project-specific test, the information should not be regarded as a promise of properties with the effect that we can be held responsible for damages resulting from the absence of features and/or properties. Our information therefore does not release customers from the obligation to carry out their own specific tests and take decisions on their own responsibility.

### Heidelberg Materials AG

Zur Anneliese 7  
59320 Ennigerloh  
Germany  
Telefon +49 2524 29-51700  
Telefax +49 2524 29-51715

